

LIP BUTTER with SHEA XP™

This emollient lip butter is formulated with **Shea XP™**, which moisturizes and nourishes lips, leaving them feeling soft.

<u>SEQUENCE</u>	<u>PERCENT</u>	<u>INGREDIENT</u>	<u>INCI NAME</u>
1	52.30	Shea XP™ (Sonneborn, LLC)	Petrolatum USP (and) Butyrospermum Parkii (Shea) Butter
1	31.20	Lexol GT-865 (Inolex Chemical Company)	Caprylic/Capric Triglyceride
1	4.00	Kahlwax 6103 (DeWolf Chemical)	Synthetic Beeswax
1	1.50	Lipex Cocoasoft (AAK)	Theobroma Cacao (Cocoa) Seed Butter
1	8.00	Kahlwax 2039L (DeWolf Chemical)	Euphorbia Cerifera (Candelilla) Wax
1	2.00	Kahlwax 2442 (DeWolf Chemical)	Copernica Cerifera (Carnauba) Wax
1	0.50	Rosamox (Kemin)	Helianthus Annuus (Sunflower) Seed Oil (and) Rosmarinus Officinalis (Rosemary) Extract
1	0.50	Monoï Oil (Centerchem, Inc.)	Cocos Nucifera (Coconut) Oil (and) Gardenia Tahitensis Flower Extract

PROCEDURE:

1. In main beaker, combine Sequence #1 ingredients and heat to 80 °C.
2. Mix until clear and all solids have melted.
3. Begin cooling to 65 °C.
4. Pour into lip balm sticks at 60 °C - 65 °C.

SPECIFICATIONS:

pH: N/A
Viscosity: N/A

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

LIP BUTTER with SHEA XP™

This emollient lip butter is formulated with **Shea XP™**, which moisturizes and nourishes lips, leaving them feeling soft.

<u>SEQUENCE</u>	<u>PERCENT</u>	<u>INGREDIENT</u>	<u>FUNCTION</u>
1	52.30	Shea XP™ (Sonneborn, LLC)	
1	31.20	Lexol GT-865 (Inolex Chemical Company)	Emollient
1	4.00	Kahlwax 6103 (DeWolf Chemical)	Provides structure
1	1.50	Lipex Cocoasoft (AAK)	Cocoa butter with improved crystallization properties and improved temperature stability
1	8.00	Kahlwax 2039L (DeWolf Chemical)	Provides structure
1	2.00	Kahlwax 2442 (DeWolf Chemical)	Provides structure
1	0.50	Rosamox (Kemin)	Anti-oxidant
1	0.50	Monoil Oil (Centerchem, Inc.)	Botanical extract

PROCEDURE:

1. In main beaker, combine Sequence #1 ingredients and heat to 80 °C.
2. Mix until clear and all solids have melted.
3. Begin cooling to 65 °C.
4. Pour into lip balm sticks at 60 °C - 65 °C.

SPECIFICATIONS:

pH: N/A
Viscosity: N/A

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.