

MICROCRYSTALLINE WAX SPECIFICATIONS

Product	Melting Point °C ASTM D-127	Congealing Point °C ASTM D-938	Needle Penetration mm x 0.1 @ 25°C ASTM D-1321	Viscosity mm²/s @ 100 °C ASTM D-445	Colour ASTM D-1500
Multiwax 180 M-H	82 - 87	74 - 79	15 - 20	13 - 18	2.0 max.
Witcotack 143	81 - 86	73 - 79	17 - 22	13 - 18	2.0 max.
Multiwax ML 445-H	79 - 84	71 - 76	25 - 32	13 - 18	2.0 max.
Witcovar 146	78 - 83	69 - 74	37 - 42	13 - 18	2.0 max.
Multiwax X 145 AH	64 - 69	63 - 68	35 - 45	13 - 18	1.0 max.