

TYPICAL PROPERTIES OF STANDARD PHARMACEUTICAL GRADE PETROLATUMS

Product	Drop Melting	Drop	Congeaing	Cone Penetration	Lovibond	Purity				
	Point °C	Point °C	Point °C	mm x 0.1 @ 25°C	Colour 2" Cell	BP	FDA	DAB	FC	
	ASTM D-127	acc. EuP	ASTM D-938	ASTM D-937	(* = 1/2" Cell)	USP				
WHITE										
Snowwhite P1™	58 - 64	51	48 - 54	180 - 200	0.5 Y Max.	■	■	■	■	
Protopet® White 1 SH	58 - 64	51	47 - 53	180 - 210	1.0 Y Max.	■	■	■	■	
Fonoline® White H	50 - 56	46	45 - 51	210 - 245	1.0 Y Max.	■	■	■		
Snowwhite N™	54 - 60	50	47 - 53	160 - 180	1.5 Y Max.	■				
Snowwhite MD™	55 - 61	53	48 - 54	160 - 180	1.0 Y Max.	■	■	■		
Snowwhite T5™	60 - 66	53	50 - 56	160 - 180	1.5 Y Max.	■				
Snowwhite Special™	53 - 59	52	47 - 53	160 - 180	1.0 Y Max.	■				
Snowwhite A4™	53 - 59	52	47 - 53	160 - 180	1.0 Y Max.	■		■		
Snowwhite EC™	58 - 66	52	49 - 56	160 - 180	2.0 Y Max.	■				
Snowwhite XH™	61 - 66	53	51 - 56	140 - 160	1,5 Y Max.	■				
Microwax MA™	61 - 68	53	56 - 62	35 - 45	2.0 Y Max.	■				
YELLOW										
Blond™	58 - 65	51	50 - 56	160 - 180	15 Y + 1.5 R*	■				
Yellow Super™	58 - 65	53	50 - 56	160 - 180	5.0 Y + 0.5 R*	■				
Extra Light Yellow™	58 - 65	51	49 - 55	160 - 180	15 Y + 1.5 R*	■				

TYPICAL PROPERTIES OF STANDARD TECHNICAL GRADE PETROLATUMS

Product	Drop Melting	Congeaing	Cone Penetration	Colour
	Point °C	Point °C	mm x 0.1 @ 25°C	
	ASTM D-127	ASTM D-938	ASTM D-937	
Yellow Technical Petrolatum I	55 - 65	48 - 56	160 - 180	yellow/brown
Amber Technical II	70 - 80	62 - 72	90 - 115	yellow/brown
Petrolatum 68	69 - 79	61 - 69	70 - 90	brown
Petrolatum 640/20	35 - 45	35 - 43	175 - 195	brown