

PLASTICS OILS PROPERTIES

		HYDROBRITE® 380 EU	PLASTIC OIL 330
PROPERTIES GUARANTEED	TEST METHOD		
Density @ 20°C, kg/m ³	ASTM D-1298	850 - 880	850 - 880
Kinematic Viscosity @ 40°C, cSt	ASTM D-445	66 - 75	66 - 75
Carbonizable Substances	Eur. Pharm.	PASS	PASS
Color, saybolt	ASTM D-156	+30 Min.	+30 Min.
Distillation, 5%, °C @ 10 mmHg	ASTM D-1160	—	278 Min.
Pour Point, °C	ASTM D-97	-9 Max.	-9 Max.
Paraffinic Carbon, %	ASTM D-3238	65 - 75	65 - 75
Naphthenic Carbon, %	ASTM D-3238	35 - 25	35 - 25
Flash Point, COC, °C	ASTM D-92	220 Min.	220 Min.