

# Petrolatum 68

## Technical Petroleum Jelly

### ▪ Physical Properties

Properties	Unit	Method	Specification	Typical
Drop melting point	°C	ASTM D 127	69-79	74
Cone penetration at 25°C	dmm	ASTM D 37	70-90	83
Congealing point	°C	ASTM D 938	61-69	68
Colour		ASTM D 1500		Brown

---

Revision date: June 1, 2015

The information presented herein is based on the best data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our product or products; nor shall anything contained herein be constructed to constitute a permission or recommendation to practice any invention covered by a patent owned by Sonneborn Refined Products B.V., any of its division, or by other, without a license from the owner of the patent