

Product Data Sheet

Witcogel[®] TCV 75 Telephone Cable Compound

▪ Product Description

TCV 75 telephone cable compound has been developed especially in order to meet a drain-test at 50-65°C (122-149°F), depending among others on filling temperatures, conductor/cable diameter and other filling conditions.

Owing to the minimum Drop Melting Point of 80°C (176°F), TCV 75 is recommended for use in cables destined for tropical and sub-tropical regions. Moreover, it meets the requirements of the BPO, Bundespost, France Telecom and others, making it a very universal filling compound. It easily can be filled into the cable in solid state at temperatures of about 30-40°C (86-104°F) below the melting point and in liquid state just above the melting point.

Properties	Unit	Method	Specification	Typical
Viscosity at 100°C	mm ² /s	ASTM D 445	Min. 18	21
Colour		ASTM D 1500	Max. 5.0	4.0
Drop Melting Point	°C	ASTM D 127	Min. 73	75
Dropping Point, on a sample conditioned as for Cone Penetration (ASTM D 937)	°C	ASTM D 566 (DIN 51801 Bl. 1)	Min. 80	82
Cone Penetration at 25°C	0.1 mm	ASTM D 937	50-70	55
COC Flash Point	°C	ASTM D 92	Min. 230	290
Relative Permittivity at 20°C	50 Hz	ASTM D 150	Max. 2.3	2,25
Volume Resistivity at 100°C	Gohm.m	ASTM D 1169	Min. 20	150
Plasticity -10°C		IEC 811.5.6	Pass	Pass
Requirements Bundespost -VDE 0472/807/C Germany			Pass	Pass
Requirements M 142 BPO) Requirements RTT (Belgium)			Pass	Pass
Requirements FT NF C 93-526, Annex C			Pass	Pass

Revision date: March 1, 2012

The information presented herein is based on the best data available and is believed to be correct. However, nothing stated in this bulletin is to be taken as a warranty, expressed or implied, regarding the accuracy of the information or the use of our product or products; nor shall anything contained herein be constructed to constitute a permission or recommendation to practice any invention covered by a patent owned by Sonneborn Refined Products B.V., any of its division, or by other, without a license from the owner of the patent