

Specifications for  
**FLOODING COMPOUND 683**

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
MELTING POINT, °F	ASTM D127	200 Min.
VISCOSITY @ 302°F, SUS	ASTM D2161	1700/1800
SLUMP/FLOW TEST, 2 hrs/176°F	LATM 040	PASS
D.C. VOLUME RESISTIVITY, OHM-cm	ASTM D257	1X10 <sup>13</sup> Min.
DIELECTRIC CONSTANT	ASTM D150	2.25 Max.
DISSIPATION FACTOR @ 1MHZ	ASTM D150	0.0010 Max.
COLOR	ASTM D1500	2.5 Max.

TYPICAL PROPERTIES FOR FLOODING COMPOUND RR683

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
CONE PENETRATION, dmm	ASTM D937	40

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.