

Specifications for  
**FLOODING COMPOUND 683**

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Melting Point, °F	ASTM D127	200 Min.
Viscosity @ 302°F, SUS	ASTM D2161	1700/1800
Slump/Flow Test, 2 hrs/176°F	LATM 040	PASS
D.C. Volume Resistivity, OHM-cm	ASTM D257	1X10 <sup>13</sup> Min.
Dielectric Constant	ASTM D150	2.25 Max.
Dissipation Factor @ 1MHZ	ASTM D150	0.0010 Max.
Color	ASTM D1500	2.5 Max.

TYPICAL PROPERTIES FOR FLOODING COMPOUND 683

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>TYPICAL VALUE</u>
Cone Penetration, dmm	ASTM D937	40