

## Specifications for **LP-200**

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
API Gravity @ 60°F	LATM 069	26.6/30.2
Specific Gravity @ 60°F/60°F	ASTM D4052	.875/.895
Visc. Saybolt @ 100°F, SUS	ASTM D2161	190/210
Visc. Saybolt @ 210°F, SUS	ASTM D2161	43.5/45.5
Acidity	USP (current revision)	PASS
Solid Paraffin	USP (current revision)	PASS
Limit Of Polycyclic Aromatic Hydrocarbons	USP (current revision)	PASS
Sulfur Compounds	USP (current revision)	PASS
Odor	LATM 092	NONE
Color, Saybolt	ASTM D156	30 Min.
Breakdown Time, Minutes	LATM 017	40 Min.
Pour Point, °C	ASTM D97	-39 Max.
Floc Point, °F	LATM 062	-34 Max.
Aniline Point, °F	ASTM D611	212/222
Dielectric Strength, KV	ASTM D877	35 Min.
Water, ppm	ASTM D6304	35 Max.
Residual Solvents, Reportable Quantity	USP 467	None
Infrared Absorption	USP 197F	Pass

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.