

## Specifications for PD-23

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Specific Gravity @ 60°F/60°F	ASTM D4052	0.795/0.810
Kinematic Visc. @ 100°F, mm <sup>2</sup> /s	ASTM D445	2.9 Max.
Saybolt Visc. @ 100°F, SUS	ASTM D2161	34.0/36.0
UV Absorbance	21CFR 178.3620(b)	PASS
Color, Saybolt	ASTM D156	30 Min.
Breakdown Time, Minutes	LATM 017	40 Min.
Flash Point, COC, °F	ASTM D92	225 Min.
Distillation, 5%, °C	ASTM D2887	215 Min.
Distillation, 95%, °C	ASTM D2887	305 Max.

PD-23 meets the Low Vapor Pressure – Volatile Organic Compounds (LVP-VOC ) exemption criteria under the California Air Resource Board (CARB) Method 310 section 3.6.2. It meets the boiling point threshold (>216°C) as defined in Method 310, using ASTM D86-11. As such PD-23 may be considered a non-reportable VOC in calculations of the VOC contents of regulated consumer product categories in the California Consumer Product Regulations.

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.