

Specification for
Shea XP®

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Melting Point, °C	ASTM D127	43.0/60.0
Consistency	ASTM D937	130/210
Kinematic Viscosity @ 100°C, cSt	ASTM D445	5.0/10.0
Odor	LATM 093	PASS
Lovibond Color, 2 IN. CELL	IP 17	5.0 Max
Congealing Point, °F	ASTM D938	95 Min

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.