

Specifications for SONNECONE[®] CM

<u>PROPERTIES GUARANTEED</u>	<u>TEST METHOD</u>	<u>LIMITS</u>
Specific Gravity @ 60°C/25°C	LATM 128	0.815/0.880
Lovibond Color, 3" CELL, Y	IP 17	1.0 Max
Melting Point, °C	ASTM D127	38.0/51.6
Melting Point, °F	ASTM D127	100.4/125.0
Odor Rating, Panel Average	LATM 093	1.0 Max.
Consistency	ASTM D937	240/300
Residue On Ignition	USP (current revision)	0.05 Max
Alkalinity	USP (current revision)	PASS
Acidity	USP (current revision)	PASS
Color	USP (current revision)	PASS
Fixed Oils, Fats, And Rosin	USP (current revision)	PASS
Organic Acids	USP (current revision)	PASS
Residual Solvents, Reportable Quantity	USP 467	NONE

This product is a White Petrolatum USP meeting requirements for USP (current revision) and FDA requirements as per 21 CFR 172.880.

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.